

Tubes type 1247 - polyvinylchlorid tubes for technical or laboratory use. The tubes can be machined and shaped. Tubes can be handled in temperatures from +5 °C to +40 °C, for a short time to +60 °C. At temperatures below 0 °C, the material becomes brittle and there is a risk of tube rupture. It is therefore not advisable to mount and mechanically strain the tubes for these reasons.

Tab. no. 1: Tubes dimensions

Outer diameter [mm]		Wall thickness [mm]		Length 1 ks [mm]	Inf. wight [g.m ⁻¹]
d	allowance deviation	t	allowance deviation		
16	+0,3	1,8	+0,4	4000 ± 10 2000 ± 10	0,12
20	+0,3	1,5	+0,4		0,13
20	+0,3	2,3	+0,5		0,19
25	+0,3	1,5	+0,4		0,17
25	+0,3	1,9	+0,4		0,21
25	+0,3	2,8	+0,5		0,29

